

PC CD-175

GRS Post-Consumer-Recycled PC Certification.

Application-Compounding PC alloy for thin-wall electronic products, home appliance(white color or light color).

性質 PROPERTIES		測試條件 CONDITION	測試方法 METHOD	單位 UNIT	數據 RESULT
熱性質	THERMAL				
熔融指數	Melt Flow Index	300°C*1.2kg	ASTM D1238	g/10min	>60
熱變形溫度	Heat Distortion Temp.	1.82 Mpa	ASTM D638	°C	≥118
機械特性	MECHANICAL				
抗張強度	Tensile Strength	5.00 cm/min	ASTM D638	MPa(kg/cm²)	≥49(500)
延伸率	Tensile Elongation	5.00 cm/min	ASTM D638	%	-
彎曲強度	Flexural Strength	3.00 cm/min	ASTM D790	MPa(kg/cm²)	≥80(800)
彎曲彈性係數	Flexural Modulus	3.00 cm/min	ASTM D790	MPa(kg/cm²)	≥2100(21000)
衝擊強度	IZOD Impact Strength	3.2 mm/23°C	ASTM D256	J/M(Kg/cm-cm)	≥50(5)
硬度	Hardness		ASTM D2240	Shore D	≥D-78
其他	OTHER				
灰份	Ash Content	800°C	ASTM D2584	%	≤0.1
比重	Specific Gravity	23°C	ASTM D792	g/cm³	1.195
含水率	Moisture Absorption	23°C	ASTM D570	%	≤0.3

These are typical properties only and are not to be constructed as specification.
Users should confirm results be their own tests.



國塑塑膠工業股份有限公司
Guo Su Plastic Industry CO.,LTD

台灣台南市官田區二鎮里成功街85號
No.85, Chenggong Street, Guantian District,
Tainan City 72046, Taiwan

TEL | +886-6-693-5077

FAX | +886-6-693-5086